SAMSUNG ELECTRO-MECHANICS

RoHS+Halogen Compliant ecoparts

SPECIFICATION

- **Supplier : Samsung electro-mechanics**
- **Product : Multi-layer Ceramic Capacitor**
- **Samsung P/N : CL05A104MP5NNNC**
- **Description : CAP, 100㎌, 10V, ±20%, X5R, 0402**

A. Samsung Part Number

CL	05	A	104	M	P	5	N	N	N	C
①	②	③	④	⑤	⑥	⑦	⑧	⑨	⑩	⑪

①	**Series**	Samsung Multi-layer Ceramic Capacitor			
②	**Size**	0402 (inch code)	L: 1.0 ± 0.05 mm	W: 0.5 ± 0.05 mm	
③	**Dielectric**	X5R	⑧	**Inner electrode**	Ni
④	**Capacitance**	100 ㎌		**Termination**	Cu
⑤	**Capacitance tolerance**	±20 %		**Plating**	Sn 100% (Pb Free)
			⑨	**Product**	Normal
⑥	**Rated Voltage**	10 V	⑩	**Special**	Reserved for future use
⑦	**Thickness**	0.5 ± 0.05 mm	⑪	**Packaging**	Cardboard Type, 7" reel

B. Samsung Reliablility Test and Judgement condition

	Performance	Test condition
Capacitance	Within specified tolerance	1㎑±10% 1.0±0.2Vrms
Tan δ (DF)	0.05 max.	
Insulation Resistance	10,000Mohm or 100Mohm·㎌ Whichever is Smaller	Rated Voltage 60~120 sec.
Appearance	No abnormal exterior appearance	Microscope (×10)
Withstanding Voltage	No dielectric breakdown or mechanical breakdown	250% of the rated voltage
Temperature Characterisitcs	X5R (From -55℃ to 85℃, Capacitance change shoud be within ±15%)	
Adhesive Strength of Termination	No peeling shall be occur on the terminal electrode	500g·F, for 10±1 sec.
Bending Strength	Capacitance change : within ±12.5%	Bending to the limit (1mm) with 1.0mm/sec.
Solderability	More than 75% of terminal surface is to be soldered newly	1) Sn63Pb37 solder 235±5℃, 5±0.5sec. 2) SnAg3.0Cu0.5 solder 245±5℃, 3±0.3sec. (preheating : 80~120℃ for 10~30sec.)
Resistance to Soldering heat	Capacitance change : within ±7.5% Tan δ, IR : initial spec.	Solder pot : 270±5℃, 10±1sec.

	Performance	Test condition
Vibration Test	Capacitance change : within ±5% Tan δ, IR : initial spec.	Amplitude : 1.5mm From 10㎐ to 55㎐ (return : 1min.) 2hours × 3 direction (x, y, z)
Humidity	Capacitance change : within ±12.5% Tan δ : 0.075 max IR : 1000Mohm or 50Mohm · ㎌ Whichever is Smaller	40±2℃, 90~95%RH, 500+12/-0hrs
Moisture Resistance	Capacitance change : within ±12.5% Tan δ : 0.075 max IR : 500Mohm or 25Mohm · ㎌ Whichever is Smaller	With rated voltage 40±2℃, 90~95%RH, 500+12/-0hrs
High Temperature Resistance	Capacitance change : within ±12.5% Tan δ : 0.075 max IR : 1000Mohm or 50Mohm · ㎌ Whichever is Smaller	With 200% of the rated voltage Max. operating temperature 1000+48/-0hrs
Temperature Cycling	Capacitance change : within ±7.5% Tan δ, IR : initial spec.	1 cycle condition Min. operating temperature → 25℃ → Max. operating temperature → 25℃ 5 cycle test

C. Recommended Soldering method :

Reflow (Reflow Peak Temperature : 260+0/-5℃, 10sec. Max)

* For the more detail Specification, Please refer to the Samsung MLCC catalogue.